

PRODUCT SHEET

LAND BIS S3 SRC

 Prod. Ref.
 25510-000

 Safety cat.
 S3 SRC

 Range of sizes
 36 - 48 (3 - 13)

 Weight (sz. 8)
 650 g

 Shape
 B

 Width (3 - 6)
 10

 Width (6,5 - 13)
 11

Description: Mud water repellent Pull-Up Nubuck ankle boot, **TEXELLE** lining, antistatic, anti-shock, slipping resistant, non metallic **APT Plate** midsole **Zero Perforation**.

Plus: AIR footbed, made of EVA and fabric, antistatic, anatomic, holed. It guarantees high stability thanks to its different kinds of thickness in the plantar area. Arch support made of polycarbonate and fibreglass conveniently placed between heel and sole, which provides support and protection of the plantar arch, thus preventing harmful bendings. Bellows tongue. Padded collar. Perfumed sole.

Suggested uses: Construction, maintenance, industries.

Care and maintenance: Clean after each use and dry off away from direct heat; treat the leather with a suitable shoe-polish. Avoid contact with aggressive chemicals or extreme temperature. Avoid immersion in sea water, lime water or cement mixed with water.

Clause



Cofra

MATERIALS / ACCESSORIES

SAFETY TECHNICAL SPECIFICATIONS

			EN ISO 20345:2011	Description	Unit	result	Requirement
Complete shoe	Toe cap: steel made, varnished with epoxy resin, impact resistant until 200 J		5.3.2.3	Shock resistance (clearance after shock)	mm	15,5	≥ 14
	ar	nd compression resistant until 1500 kg	5.3.2.4	Compression resistance (clearance after compression)	mm	15	≥ 14
	Anti perforat	ion midsole: in multi-layers highly tensile fabric, penetration resistant, Zero Perforation	6.2.1	Penetration resistance	N	To 1100 N	≥ 1100
						No Perforation	
	Antistatic shoe: the bottom is fit for the dissipation of electrostatic charges		6.2.2.2	Electric resistance			
				- wet	$M\Omega$	21	≥ 0.1
				- dry	$M\Omega$	66	≤ 1000
	Energy abso	rption system: polyurethane low density and heel profile	6.2.4	Shock absorption	J	> 34	≥ 20
Upper	Mud water repellent Pull-Up Nubuck		5.4.6	Water vapour permeability	mg/cmq h	> 4,2	≥ 0,8
	thickness 1,6/1,8 mm			Permeability coefficient	mg/cmq	> 42,9	> 15
			6.3.1	Water absorption		28%	≤ 30%
				Water penetration		0,0 g	$\leq 0.2 g$
Vamp	Felt, breathable, colour dark grey		5.5.3	Water vapour permeability	mg/cmq h	> 4,7	≥ 2
lining	thickness 1,2 mm			Permeability coefficient	mg/cmq	> 40,6	≥ 20
Quarter	TEXELLE, breathable, abrasion resistant, colour brown thickness 1,2 mm		5.5.3	Water vapour permeability	mg/cmq h	> 6,8	≥ 2
lining				Permeability coefficient	mg/cmq	> 55,4	≥ 20
Sole	Antistatic dual-density polyurethane directly injected in the upper:		5.8.3	Abrasion resistance (lost volume)	mm³	88	≤ 150
	Outsole:	black, high density, slipping resistant, abrasion	5.8.4	Flexing resistance (cut increase)	mm	1	≤ 4
		resistant and hydrocarbons resistant,	5.8.6	Interlayer bond strength	N/mm	> 5	≥ 4
	Midsole:	brown, low density, comfortable and anti-shock	6.4.2	Hydrocarbons resistance (ΔV = volume increase)	%	0,5	≤ 12
	Adherence coefficient of the sole		5.3.5	SRA : ceramic + detergent solution – flat		0,57	≥ 0,32
				SRA : ceramic + detergent solution – heel (contact angle	7°)	0,52	≥ 0,28
				SRB : steel + glycerol – flat		0,22	≥ 0,18
				SRB : steel + glycerol – heel (contact angle 7°)		0,18	≥ 0,13