



Prod. Ref.	25550-001
Safety cat.	S3 SRC
Range of sizes	37 - 47 (4 - 12)
Weight (sz. 8)	685 g
Shape	B
Width (4 - 6)	10
Width (6,5 - 12)	11

Description: Yellow water repellent nubuck ankle boot, **TEXELLE** lining, antistatic, anti-shock, slipping resistant, non metallic **APT Plate** midsole **Zero Perforation**.

Plus: **AIR** footbed, made of EVA and fabric, antistatic, anatomic, holed. It guarantees high stability thanks to its different kinds of thickness in the plantar area. Arch support made of polycarbonate and fibreglass conveniently placed between heel and sole, which provides support and protection of the plantar arch, thus preventing harmful bendings. Bellows tongue. Padded collar. Perfumed sole.

Suggested uses: Construction, maintenance, industries.

Care and maintenance: Clean after each use and dry off away from direct heat; treat the leather with a suitable shoe-polish. Avoid contact with aggressive chemicals or extreme temperature. Avoid immersion in sea water, lime water or cement mixed with water.

MATERIALS / ACCESSORIES

Complete shoe	Toe cap: steel made, varnished with epoxy resin, impact resistant until 200 J and compression resistant until 1500 kg
	Anti perforation midsole: in multi-layers highly tensile fabric, penetration resistant, Zero Perforation
	Antistatic shoe: the bottom is fit for the dissipation of electrostatic charges
Upper	Energy absorption system: polyurethane low density and heel profile
	Yellow water repellent nubuck thickness 1,6/1,8 mm
Vamp	Felt, breathable, colour dark grey
lining	thickness 1,2 mm
Quarter	TEXELLE , breathable, abrasion resistant, colour dark yellow
lining	thickness 1,2 mm
Sole	Antistatic dual-density polyurethane directly injected in the upper:
	Outsole: crep, high density, slipping resistant, abrasion resistant and hydrocarbons resistant, Midsole: beige, low density, comfortable and anti-shock Adherence coefficient of the sole

SAFETY TECHNICAL SPECIFICATIONS

Clause EN ISO 20345:2011	Description	Unit	Cofra result	Requirement
5.3.2.3	Shock resistance (clearance after shock)	mm	15,5	≥ 14
5.3.2.4	Compression resistance (clearance after compression)	mm	15	≥ 14
6.2.1	Penetration resistance	N	To 1100 N	≥ 1100
			No Perforation	
6.2.2.2	Electric resistance			
	- wet	MΩ	21	≥ 0,1
	- dry	MΩ	66	≤ 1000
6.2.4	Shock absorption	J	> 34	≥ 20
5.4.6	Water vapour permeability	mg/cmq h	> 4,3	≥ 0,8
	Permeability coefficient	mg/cmq	> 42,6	> 15
6.3.1	Water absorption		14%	≤ 30%
	Water penetration		0,0 g	≤ 0,2 g
5.5.3	Water vapour permeability	mg/cmq h	> 4,5	≥ 2
	Permeability coefficient	mg/cmq	> 39,2	≥ 20
5.5.3	Water vapour permeability	mg/cmq h	> 6,8	≥ 2
	Permeability coefficient	mg/cmq	> 55,4	≥ 20
5.8.3	Abrasion resistance (lost volume)	mm ³	88	≤ 150
5.8.4	Flexing resistance (cut increase)	mm	1	≤ 4
5.8.6	Interlayer bond strength	N/mm	> 5	≥ 4
6.4.2	Hydrocarbons resistance (ΔV = volume increase)	%	0,5	≤ 12
5.3.5	SRA : ceramic + detergent solution – flat		0,57	≥ 0,32
	SRA : ceramic + detergent solution – heel (contact angle 7°)		0,52	≥ 0,28
	SRB : steel + glycerol – flat		0,22	≥ 0,18
	SRB : steel + glycerol – heel (contact angle 7°)		0,18	≥ 0,13